



Technical Data Sheet

Description

Tek-Coat WP is a single component water-based high performance elastomeric weather proof and decorative protective coating. It is designed to provide resistance and protection against chloride ingress. These superior properties are further enhanced by the availability of a selective range of colours for aesthetics.

Advantages

- Water-based coating
- Weather proof
- Breathable
- Formaldehyde free
- Non-flammable
- UV Resistance
- VOC complaint
- Available in selected range of RAL colors

Uses

- Anti-carbonation coating
- Bridges
- Tunnels
- Anti-chloride coating
- External weather proof coating

Physical Properties*

| Property | Typical Results |
|---------------------------------------|--|
| Water vapor transmission | >150 g/m ² .d |
| Chloride ion diffusivity | Nil |
| Reduction in chloride ion penetration | 97% |
| Reduction in water absorption | 95% |
| Water sorptivity | 0.006 mm/min ½ |
| Tear resistance | 13 Pa |
| Bond strength to concrete | Greater then cohesive strength of concrete |

| Tek-Prime AC | |
|---|-------------------------|
| Solid content | >10% active ingredients |
| Specific gravity | 0.88 @ 25°C |
| Water sorptivity | 0.007 mm/min ½ |
| Rapid chloride permeability | Low |
| Chloride ion diffusivity | Nil |
| *The above properties are average laboratory values | |

Application Properties

| | |
|-----------------------|--|
| Dry film thickness | Two coats of 150 microns DFT each coat |
| Touch dry | 6 hours at 25°C 4 hours at 35°C |
| Minimum overcoat time | 4 to 6 hours |
| Maximum overcoat time | 24 hours |
| Full cure | 7 days |

Volatile Organic Content

VOC <10g/L

Fire performance

BS 476 Part 7: Class 1 surface spread of flame

Packing

Tek-Coat WP is available in 5 lt. & 20 lt. pack.

Theoretical Coverage

8.3 square meters per litre at 150 microns WFT / DFT (2 coats recommended at above thickness)

Shelf Life

18 months when stored in cool dry environment in factory packed unopened containers.

Installation Guidelines

Spraytek provides detailed method statements on all its products for use in various applications. These must be referred to prior to starting the work. The information below is a summary intended for guidance only.

Surface Preparation

Concrete substrate must be structurally sound. Loose or unsound concrete should be removed. Surfaces must be entirely free of oil, grease, paint, corrosion deposits, dust, laitance or other surface deposits. The old substrate must be prepared to create a 'key' for bonding by high pressure water blasting. Any blow holes should be filled with **Tek-Crete FR**. The moisture content of the concrete substrate should be less than 7%.

Priming

The substrate must be primed using **Tek-Prime AC** primer and allow to dry, prior to application of **Tek-Coat WP**. Ensure that no ponding of the primer during the application and applied to appropriate thickness and it is not applied too thick. If the primed surfaces left to dry for more than 24 hours the surfaces has to re-primed.

If the concrete substrates are too porous, then it is recommended to use multiple coats of **Tek-Prime AC** to seal of the surfaces.

Mixing

Tek-Coat WP is supplied as a single component product. Make sure to shake the drum and stir the product prior to application.

Application

Apply in two coats of **Tek-Coat WP** at 150 microns per coat WFT using roller, brush or airless spray. When using airless spray, tip size should be 0.017" to 0.0020" at a preasure 2200 psi. The product can be thinned by 5%, if necessary, using clean water but the WFT should be maintained accordingly. Reocat if necessary after 4 to 16 hours at 35°C.

Precautions

Do not add any thinner or solvent.
Do not apply in wet conditions or at temperature below 3°C of the dew point.
Do not dispose into water drains.
Do not use in immersed conditions
Avoid skin contact
Apply only on to slabs that have a waterproofing system installed in order to prevent blistering due to osmosis.

Technical Support

Spraytek offers full technical support package to specifiers, contractors and end users, as well as technical assistance on site and after sales consultations.

Health & Safety

As with all chemical products, caution should always be exercised. Protective clothing, such as gloves and goggles, should be worn. See packaging/MSDS for specific instructions.

Treat any splashes to the skin or eyes with fresh water immediately. Should any of the products be accidentally swallowed, do not induce vomiting, but call for medical assistance immediately.

| | |
|-------------|-----------------|
| Reference # | TDS / STC /TCWP |
| Issue Date: | 01/2012 |
| Revision # | 1 |

The information contained herein is to the best of our knowledge, belief, and accuracy. However, hence the conditions of handling and usage beyond our control. We make no warrantee of results, and assume no responsibility or liability for any damages or consequential damage incurred by the use of the product. Our products are sold on the condition that the user shall evaluate them, as well as our recommendations. To determine their suitability for a particular purpose. The user is solely responsible for the selection of Spraytek products.



Spraytek Coatings LLC

P.O. Box 27356, Dubai, U.A.E., Tel.: +9714 2221432, Fax: +9714 2275750, Email: info@spraytek.ae

www.spraytek-me.com